

INTERNATIONAL PRODUCTS CORPORATION

201 CONNECTICUT DRIVE • PO BOX 70 • BURLINGTON, NJ 08016-0070 • USA
PHONE: 609/386-8770 • FAX: 609/386-8438 • E-MAIL: MKT@IPCOL.COM

Conductivity of P-80[®] Rubber Lubricant Emulsion

- Procedure:
- P-80 was poured on a piece of Buna N elastomer. The conductivity was measured as the water in P-80 evaporated.
 - Instrument: TDSTestr³ – Cole Parmer Instrument Company
 - Room Temperature
- Conclusion: P-80 has no conductivity after evaporation.

